

# SANDWICHELEMENT FB-4 Aluminium



## Product Information

FB-4 Aluminium

#### Description:

Aluminium sandwich elements consist of an extruded polystyrene core and, on both sides, top layers of 0.8 mm, 1.0 mm, 1.5 mm or 2.0 mm thick aluminium.The composite element is covered with a protective foil on both sides (FB-4/Blank with foil is available only at extra charge; without foil surface scratches must be expected). 10 years Stadur guarantee

#### **Properties**:

- very good heat insulation
- high intrusion security
- UV-endurance
- extremely high stability
- good sound insulation values easy
- easy to process with the usual metal working tools

#### Facings:

0.8 mm, 1.0 mm, 1.5 mm or 2.0 mm aluminium panels in white, blank, anodised or painted in all RAL and NCS colours. Further thicknesses available on request. Liquid or powder coating available

### Core Material:

Extruded polystyrene foam, CFC-free or CO2 foamed, low vapour permeability, lowest water absorbance, B1 in accordance with DIN 4102. The foam core is corrugated for optimum adhesion. No dust release during processing. Core material of different thermal conductivity λD-value 0.029 – 0.035 is available.

#### **Overall Thickness**:

24 mm - Further thicknesses (thicker / thinner) of the facing layers or the foam core available on request.

#### Formats:

 $2000 \times 1000 \text{ mm} / 2500 \times 1250 \text{ mm} / 3000 \times 1500 \text{ mm} / 4000 \times 1500 \text{ mm}$  Other formats and fixed formats are available on request

Technical Data:	Overall Thickness	Facings	U-Value (\D 0.029)	U-Value (λD 0.035)
	24	1.0 mm	1.07	1.25
	24	1.5 mm	1.12	1.29

### **Special Elements**:

Aluminium sandwich elements can be supplied with optimised sound insulation values by incorporating special sound insulation panels or with intrusion-inhibiting aluminium inserts. Edge jointing inserts of wood, plastic or aluminium and edge finishing of the foam core as a stepped rebate or tongue and groove are possible. Other core materials, e.g. polyurethane foam, mineral wool or honeycomb construction materials are available on request.

### Areas of Application:

Window panels, parapet elements, partition walls, exhibition construction, door panels, container construction, balcony cladding, boat and yacht building, facade elements, refrigeration rooms, advertising signs

#### Note:

FB-4 elements can be supplied faced on one side with painted aluminium and on the reverse side with a white Stadurlon or PVC board under the designation FB-4/SL and FB-4/PVC respectively. Due to the asymmetrical construction warping of the element can occur. With FB-4/Blank elements surface scratches must be expected due to the lack of protective foil. When using solvent-based substances, polyurethane foam must be employed as the core. For further information please refer to our brochure: Processing Instructions

The product colours and surfaces shown in this brochure are subject to printing variations. Should you require exact colour and surface characteristics we recommend that you ask for a sample. Technical changes reserved. All business transactions are subject to our general terms and conditions which can be viewed at www.stadur.com.

Stadur Produktions GmbH & Co. KG Ostereichen 2-4, 21714 Hammah, Germany, E-Mail stadur@stadur.com Revision 2016-05A Phone +49 (0) 41 44 / 234-0 Fax +49 (0) 41 44 / 234-100 www.stadur.com



