



SANDWICHELEMENT

FB-1 PVC

STADUR
MADE IN GERMANY

Product Information

FB-1 PVC



Description:

PVC sandwich elements consist of an extruded polystyrene core and, on both faces, top layers of hard PVC of 1.0 mm, 1.3, 1.5 mm or 2.0 mm thickness. The composite element is covered with a protective foil on both sides.

Properties:

- very good thermal insulation
- UV-resistant (5 years manufacturer's guarantee for the PVC facings)
- high impact resistance
- easy to process with the usual wood and metal working tools
- the sandwich element as a finished end product can be safely disposed in household waste

Facings:

Hard-PVC compact panels on both sides, 1.0 mm, 1.3, 1.5 mm or 2.0 mm Standard colour: White similar to RAL 9016 brilliant or stained Please refer to the current price list for valid formats and thicknesses of each colour.

Core Material:

Extruded polystyrene foam, CFC-free or CO2 foamed, low vapour permeability, lowest water absorbance, Fire protection class E according to EN 13501-1. The foam core is corrugated for optimum adhesion. No dust release during processing. Core material of different thermal conductivity λ D-value 0.029 - 0.035 is available.

Formats:

2000 x 1000 mm / 3000 x 1500 mm / 3000 x 2000 mm. Other formats and fixed formats are available on request.

Overall Thickness	Facings	U-Value (λ D 0,029)	U-Value (λ D 0,033)	R-Value (λ D 0,029)	R-Value (λ D 0,033)	Weight (kg/m ²)
20 mm	1.3 mm	1.29	1.43	0.6	0.53	4.20
24 mm	1.3 mm	1.11	1.21	0.74	0.66	4.33
28 mm	1.3 mm	0.95	1.06	0.88	0.78	4.47
32 mm	1.3 mm	0.84	0.94	1.02	0.9	4.6
36 mm	1.3 mm	0.75	0.84	1.15	1.02	4.73
40 mm	1.3 mm	0.68	0.76	1.29	1.14	4.86
44 mm	1.3 mm	0.62	0.7	1.43	1.26	4.99

Special Elements:

PVC Sandwich elements can be supplied with optimised sound insulation values by incorporating special sound insulation panels or with intrusion-inhibiting aluminium inserts. Other core materials (e.g. polyurethane foam) are available on request.

Areas of Application:

Window panels, parapet elements, partition walls, exhibition construction, door panels, container construction, balcony cladding, boat and yacht building, facade elements, refrigeration rooms, advertising signs

Note:

Due to the thermoplastic material properties of PVC we advise against the use of coloured facings for outdoor use. In the case of subsequently painted elements for which Stadur has given no written release any claim under the guarantee is void. Due to considerably better sound insulation values and a clearly quieter element we recommend the use of 2.0 mm facing layers. When solvent-based substances are employed, polyurethane foam must be used as the core. For further information please refer to our brochure: Processing Instructions

The product colours and surfaces shown in this brochure are subject to printing variations. Should you require exact colour and surface characteristics we recommend that you ask for a sample. Technical changes reserved. All business transactions are subject to our general terms and conditions which can be viewed at www.stadur.com.